

EMASOL

2.0 % Shade		DISPERSE DYES	Allion Count Index Disperse Dyes	PH Range	Light Fastness	Sublimation	Staining	Washing ISO Co3 (60 °C)	Rubing
		Luminous Yellow 10 G	Yellow 184	4 - 6	5 - 6	4 - 5	3 - 4	5 - 0	5 - 5
		Yellow SE-4G	Yellow 211	4 - 9	7 - 0	3 - 4	4 - 5	5 - 0	5 - 5
		Yellow GBA (Korea)	Yellow 3	4 - 5	5 - 6	4 - 0	4 - 5	4 - 5	4 - 5
		Golden Yellow GG	Orange Mix	4 - 5	5 - 6	4 - 0	4 - 5	4 - 5	4 - 5
		Orange E-3RT	Orange 25	4 - 9	4 - 5	4 - 0	3 - 4	4 - 0	4 - 5
		Scarlet GBH	Red 1	4 - 9	6 - 7	5 - 0	2 - 3	3 - 4	4 - 0
		Luminous Red G	Red 277	4 - 6	5 - 6	4 - 5	3 - 4	5 - 0	4 - 5
		Brill Red E-FB	Red 60	4 - 9	6 - 0	2 - 0	3 - 0	4 - 5	4 - 5
		Red SE-3B (Korea)	Red 343	4 - 9	6 - 7	5 - 0	3 - 0	5 - 0	5 - 5
		Rubine E-B	Red 13	4 - 9	4 - 5	5 - 0	4 - 5	3 - 4	4 - 0
		Rubine S-2GE	Red 167.1	4 - 9	6 - 7	5 - 0	4 - 5	4 - 5	4 - 5
		Violet S-3RL	Violet 63	4 - 9	6 - 7	3 - 4	3 - 0	5 - 0	4 - 5
		Turquoise S-GL (Korea)	Blue 60	4 - 9	7 - 0	4 - 0	4 - 5	5 - 0	5 - 0
		Turquoise Blue S-BL	Mix	4 - 6	5 - 0	3 - 4	3 - 0	4 - 5	4 - 5
		Blue 2-BLN	Blue 56	4 - 6	6 - 0	4 - 5	4 - 0	4 - 5	5 - 0
		Blue SE-2R (Korea)	Blue 183	4 - 9	6 - 7	5 - 6	4 - 5	5 - 0	5 - 0
		Navy S-2GL	Mix	4 - 6	6 - 0	5 - 0	4 - 5	4 - 5	5 - 0
		Navy K-BL	Mix	4 - 9	5 - 0	4 - 5	3 - 0	4 - 0	4 - 5
		Navy H-GLN	Mix	4 - 9	5 - 0	4 - 5	3 - 0	4 - 0	4 - 5

	Green SE-2B	Green 9	2 - 7	5 - 0	5 - 6	3 - 4	5 - 0	5 - 0
	Brown S-2RL (Korea)	Mix	4 - 9	5 - 0	5 - 0	4 - 5	5 - 0	4 - 5
	Brown GL (L)	Mix	4 - 6	4 - 5	4 - 5	3 - 4	4 - 5	4 - 5
	Black CR Sp	Black Unk	4 - 9	5 - 0	4 - 5	3 - 4	4 - 0	4 - 5
	Black K-B (Korea)	Black Unk	4 - 6	3 - 9	3 - 4	3 - 4	5 - 0	4 - 5